1 Tobermore

Ara Artro Constellation

220 x 50 x 80


Using a 3-way mix of Artro's 'cool' grey palette, Ara is perfect for creating distinctive schemes with contemporary tones.


The stylish finish of the blend offers a unique and modern aesthetic. The mix of the three colours will be sure to add contrast to your next project.



 Redestrian
 Light Traffic
 Commercial Traffic
 Smooth

Refer to relevant guidance in BS 7533





3. Steel





Specification

Product type	Concrete Paving Block			
Manufactured to	BS EN 1338:2003			
Surface Layer	Hard-wearing surface layer with a minimum of 4m			
Surface Finish	Smooth			
Efflorescence	Minimum 12 hour vapour curing to significantly red			
Strength	Typical tensile splitting strength of >3.6MPa			
Slip/Skid risk	Mean polished skid resistance value (PSRV) > Mean unpolished skid resistance value (USRV			
Installed to (flexibly)	BS7533-3-2005			
055	Plus Q24 110 Create 45-20-64/400			
Tolerances on Dimensions (mm)	Length ±2mm, width ±2mm, thickness ±3mm			
Abrasion Resistance	Class 3			
Durability (Freeze-thaw)	Class 3			
External Fire Performance	Deemed to satisfy. See Commission Decision 2000/			
Reaction to fire	Class A1			
Applications	Refer to the relevant part of BS7533 for the correct			
Energy used	100% renewable energy			
Water used	100% from our rainwater harvesting system and g			
Recycled content	Not less than 12%			
Carbon Footprint	20.22kgCo ² e/m ²			
Recyclable	100% of this product can be recycled			
Manufacturing & Delivery	From one location within the UK			
nreeon rating www.bre.co.uk	BREEAM – 'B' according to the Green Guide to Sp prepared recycled sub-base.			

Tobermore products are manufactured in accordance with an accredited ISO 9001:2015 Quality Management. Manufacturing facilities are accredited to ISO14001:2015 Environmental Management. The company publish environmental labels and declarations in accordance with BES 6001.

product	size (mm)	colours available	in stock	m² per pack	m² per slice		no. per pack	weight kg per pack GB	weight kg per pack NI/ROI
Artro Ara	220x55x80	Platinum, Steel & Carbon Ara Mix	YES	6.776	0.847	82.64	560	1266	1266

Contact Us GB: 0844 800 5736 NI: 028 7964 2411 ROI: 048 7964 2411

Email technical@tobermore.co.uk sales@tobermore.co.uk

\checkmark	PrimeTop °	🗾 Ef-Sto	p
--------------	-------------------	----------	---

mm and >350kgs/m³ cement

educe the possibility of efflorescence

) >45

)/553/EC

ect sub-base design. Available from www.bsigroup.com

groundwater bore hole

Specification, 4th Edition 2009. 'A', can be achieved when used in conjunction with a