

# Tucana

## Fusion Constellation

200 x 100 x 60/80

Add some warmth to your project with our Fusion Tucana mix. With a mostly sandstone finish and a hint of Mid Grey.

This signature mix can help create a modern yet traditional feel in any project. Bring some sunshine to your space with Tucana.



SCAN HERE



60mm  
80mm

Depths

1. Sandstone



2. Mid Grey



### Specification

<b>Product type</b>	Concrete Paving Block		
<b>Manufactured to</b>	<b>BS EN 1338:2003</b>	200x100x60mm	200x100x80mm
<b>Surface Layer</b>	Hard-wearing surface layer with a minimum of 4mm and >350kgs/m <sup>3</sup> cement		
<b>Surface Finish</b>	Textured Granite Aggregate		
<b>Granite Content in Surface Layer</b> (Not less than %)	<b>53%</b> Mid Grey <b>45%</b> Sandstone		
<b>Efflorescence</b>	Minimum 12 hour vapour curing to significantly reduce the possibility of efflorescence		
<b>Strength</b>	<b>BS EN 1338:2003</b>	Typical tensile splitting strength of >3.6MPa	
<b>Slip/Skid risk</b>	Mean polished skid resistance value (PSRV) >45 Mean unpolished skid resistance value (USRV) >45		
<b>Installed to</b>	<b>BS 7533-3:2005</b>	200x100x60mm	200x100x80mm
<b>NS</b>	<b>Plus</b> Q24 110 <b>Create</b> 45-20-64/400	200x100x60mm	200x100x80mm
<b>Tolerances on Dimensions (mm)</b>	Length ±2mm, width ±2mm, thickness ±3mm		
<b>Abrasion Resistance</b>	Class 3		
<b>Durability (Freeze-thaw)</b>	Class 3		
<b>External Fire Performance</b>	Deemed to satisfy. See Commission Decision 2000/553/EC		
<b>Reaction to fire</b>	Class A1		
<b>Applications</b>	Refer to the relevant part of BS 7533 for the correct sub-base design and the most suitable product size for your application. Available from <a href="http://www.bsigroup.com">www.bsigroup.com</a>		
<b>Energy used</b>	100% renewable energy		
<b>Water used</b>	100% water used from rainwater harvesting system and groundwater bore hole		
<b>Recycled content</b>	Not less than 6%		
<b>Carbon Footprint</b>	<b>60mm</b> 17.20kgCo <sup>2</sup> e/m <sup>2</sup> (+6.6%-2.0% depending on specific products) <b>80mm</b> 23.47kgCo <sup>2</sup> e/m <sup>2</sup> (+8.4%-5.8% depending on specific products)		
<b>Recyclable</b>	100% of this product can be recycled		
<b>Manufacturing &amp; Delivery</b>	From one location within the UK		
<b>breem rating</b> <a href="http://www.breem.co.uk">www.breem.co.uk</a>	<b>60mm: A</b> , according to the Green Guide to Specification, 4 <sup>th</sup> Edition 2009. <b>A+</b> , can be achieved when used in conjunction with a prepared recycled sub-base. <b>80mm: B</b> , according to the Green Guide to Specification, 4 <sup>th</sup> Edition 2009. <b>A</b> , can be achieved when used in conjunction with a prepared recycled sub-base.		
Tobermore products are manufactured in accordance with an accredited ISO 9001:2015 Quality Management. Manufacturing facilities are accredited to ISO14001:2015 Environmental Management. The company publish environmental labels and declarations in accordance with BES 6001.			

product	size (mm)	colours	in stock	m <sup>2</sup> per pack	m <sup>2</sup> per slice	no. per m <sup>2</sup>	no. per pack	weight kg per pack GB	weight kg per pack NI/ROI
<b>Fusion Tucana60mm</b>	200 x 100 x 60	Sandstone Mid Grey Tucana Mix	YES	13.44	2.24	50	672	1810	1800
<b>Fusion Tucana80mm</b>	200 x 100 x 80	Sandstone Mid Grey Tucana Mix	YES	9.6	1.6	50	480	1756	1746

# Tucana

## Fusion Constellation

300 x 200 x 60/80

Add some warmth to your project with our Fusion Tucana mix. With a mostly sandstone finish and a hint of Mid Grey.

This signature mix can help create a modern yet traditional feel in any project. Bring some sunshine to your space with Tucana.



SCAN HERE



60mm  
80mm

Depths

1. Sandstone



2. Mid Grey



### Specification

 PrimeTop  Ef-Stop

<b>Product type</b>	Concrete Paving Block	
<b>Manufactured to</b>	<b>BS EN 1338:2003</b>	300x200x80mm
	<b>BS EN 1339:2003</b>	300x200x60mm
<b>Surface Layer</b>	Hard-wearing surface layer with a minimum of 4mm and >350kgs/m <sup>3</sup> cement	
<b>Surface Finish</b>	Textured Granite Aggregate	
<b>Granite Content in Surface Layer</b> (Not less than %)	<b>53%</b> Mid Grey	<b>45%</b> Sandstone
<b>Efflorescence</b>	Minimum 12 hour vapour curing to significantly reduce the possibility of efflorescence	
<b>Strength</b>	<b>BS EN 1338:2003</b>	Typical tensile splitting strength of >3.6MPa
	<b>BS EN 1339:2003</b>	Typical tensile splitting strength of >5MPa (Class 3)
<b>Slip/Skid risk</b>	Mean polished skid resistance value (PSRV) >45 Mean unpolished skid resistance value (USRV) >45	
<b>Installed to</b>	<b>BS 7533-3:2005</b>	300x200x80mm
	<b>BS 7533-4:2006</b>	300x200x60mm
<b>NS</b>	<b>Plus Q24 110</b>	300x200x80mm
	<b>Create 45-20-64/400</b>	
<b>NS</b>	<b>Plus Q25 315</b>	300x200x60mm
	<b>Create 45-20-64/395</b>	
<b>Tolerances on Dimensions (mm)</b>	Length ±2mm, width ±2mm, thickness ±3mm	
<b>Abrasion Resistance</b>	Class 3	
<b>Durability (Freeze-thaw)</b>	Class 3	
<b>External Fire Performance</b>	Deemed to satisfy. See Commission Decision 2000/553/EC	
<b>Reaction to fire</b>	Class A1	
<b>Applications</b>	Refer to the relevant part of BS 7533 for the correct sub-base design and the most suitable product size for your application. Available from <a href="http://www.bsigroup.com">www.bsigroup.com</a>	
<b>Energy used</b>	100% renewable energy	
<b>Water used</b>	100% water used from rainwater harvesting system and groundwater bore hole	
<b>Recycled content</b>	Not less than 6%	
<b>EPD Carbon Footprint</b>	<b>60mm</b> 17.20kgCO <sub>2</sub> e/m <sup>2</sup> (+6.6% -2.0% depending on specific products) <b>80mm</b> 23.47kgCO <sub>2</sub> e/m <sup>2</sup> (+8.4% -5.8% depending on specific products)	
<b>Recyclable</b>	100% of this product can be recycled	
<b>Manufacturing &amp; Delivery</b>	From one location within the UK	
<b>Breem rating</b> <a href="http://www.breem.co.uk">www.breem.co.uk</a>	<b>60mm: A</b> , according to the Green Guide to Specification, 4 <sup>th</sup> Edition 2009. <b>A+</b> can be achieved when used in conjunction with a prepared recycled sub-base. <b>80mm: B</b> , according to the Green Guide to Specification, 4 <sup>th</sup> Edition 2009. <b>A</b> can be achieved when used in conjunction with a prepared recycled sub-base.	

Tobermore products are manufactured in accordance with an accredited ISO 9001:2015 Quality Management. Manufacturing facilities are accredited to ISO14001:2015 Environmental Management. The company publish environmental labels and declarations in accordance with BES 6001.

product	size (mm)	colours available	in stock	m <sup>2</sup> per pack	m <sup>2</sup> per slice	no. per m <sup>2</sup>	no. per pack	weight kg per pack GB	weight kg per pack NI/ROI
<b>Fusion Tucana60mm</b>	300 x 200 x 60	Sandstone Mid Grey Tucana Mix	YES	12.48	3.12	16.66	208	1765	1755
<b>Fusion Tucana80mm</b>	300 x 200 x 80	Sandstone Mid Grey Tucana Mix	YES	9.6	2.4	16.66	160	1756	1746

**Contact Us**

GB: 0844 800 5736  
NI: 028 7964 2411  
ROI: 048 7964 2411

**Email**

technical@tobermore.co.uk  
sales@tobermore.co.uk

# Tucana

## Fusion Constellation


600 x 300 x 60/80

Add some warmth to your project with our Fusion Tucana mix. With a mostly sandstone finish and a hint of Mid Grey.

This signature mix can help create a modern yet traditional feel in any project. Bring some sunshine to your space with Tucana.



SCAN HERE



60mm  
80mm  
Depths

1. Sandstone



2. Mid Grey



### Specification

<b>Product type</b>	Concrete Paving Flag		
<b>Manufactured to</b>	<b>BS EN 1339:2003</b>	600x300x60mm	600x300x80mm
<b>Surface Layer</b>	Hard-wearing surface layer with a minimum of 4mm and >350kgs/m <sup>3</sup> cement		
<b>Surface Finish</b>	Textured Granite Aggregate		
<b>Granite Content in Surface Layer</b> (Not less than %)	<b>53%</b> Mid Grey <b>45%</b> Sandstone		
<b>Efflorescence</b>	Minimum 12 hour vapour curing to significantly reduce the possibility of efflorescence		
<b>Strength</b>	<b>BS EN 1338:2003</b>	Typical tensile splitting strength of >3.6MPa	
	<b>BS EN 1339:2003</b>	Typical tensile splitting strength of >5MPa (Class 3)	
<b>Slip/Skid risk</b>	Mean polished skid resistance value (PSRV) >45 Mean unpolished skid resistance value (USRV) >45		
<b>Installed to</b>	<b>BS 7533-4:2006</b>	600x300x60mm	600x300x80mm
<b>NS</b>	<b>Plus</b> Q25 315 <b>Create</b> 45-20-64/395	600x300x60mm	600x300x80mm
<b>Tolerances on Dimensions (mm)</b>	Length ±2mm, width ±2mm, thickness ±3mm		
<b>Abrasion Resistance</b>	Class 3		
<b>Durability (Freeze-thaw)</b>	Class 3		
<b>External Fire Performance</b>	Deemed to satisfy. See Commission Decision 2000/553/EC		
<b>Reaction to fire</b>	Class A1		
<b>Applications</b>	Refer to the relevant part of BS 7533 for the correct sub-base design and the most suitable product size for your application. Available from <a href="http://www.bsigroup.com">www.bsigroup.com</a>		
<b>Energy used</b>	100% renewable energy		
<b>Water used</b>	100% water used from rainwater harvesting system and groundwater bore hole		
<b>Recycled content</b>	Not less than 6%		
<b>Carbon Footprint</b>	<b>60mm</b> 17.20kgCo <sub>2</sub> e/m <sup>2</sup> (+6.6% -2.0% depending on specific products) <b>80mm</b> 23.47kgCo <sub>2</sub> e/m <sup>2</sup> (+8.4% -5.8% depending on specific products)		
<b>Recyclable</b>	100% of this product can be recycled		
<b>Manufacturing &amp; Delivery</b>	From one location within the UK		
<b>breem rating</b> <a href="http://www.bre.co.uk">www.bre.co.uk</a>	<b>60mm: A</b> , according to the Green Guide to Specification, 4 <sup>th</sup> Edition 2009. <b>A+</b> , can be achieved when used in conjunction with a prepared recycled sub-base. <b>80mm: B</b> , according to the Green Guide to Specification, 4 <sup>th</sup> Edition 2009. <b>A</b> , can be achieved when used in conjunction with a prepared recycled sub-base.		
Tobermore products are manufactured in accordance with an accredited ISO 9001:2015 Quality Management. Manufacturing facilities are accredited to ISO14001:2015 Environmental Management. The company publish environmental labels and declarations in accordance with BES 6001.			

product	size (mm)	colours available	in stock	m <sup>2</sup> per pack	m <sup>2</sup> per slice	no. per m <sup>2</sup>	no. per pack	weight kg per pack GB	weight kg per pack NI/ROI
<b>Fusion Tucana 60mm</b>	600 x 300 x 60	Sandstone Mid Grey Tucana Mix	YES	9.36	4.68	5.55	52	1325	1315
<b>Fusion Tucana 80mm</b>	600 x 300 x 80	Sandstone Mid Grey Tucana Mix	YES	7.2	3.6	5.55	40	1319	1309